



Rec'd PCT/PTO 14 JAN 2005  
PCT/GB2003/003086 #2



INVESTOR IN PEOPLE

The Patent Office  
Concept House  
Cardiff Road  
Newport  
South Wales  
NP10 8QQ

REC'D 14 AUG 2003

WIPO PCT


**PRIORITY  
DOCUMENT**  
SUBMITTED OR TRANSMITTED IN  
COMPLIANCE WITH RULE 17.1(a) OR (b)

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.




Signed

Dated

5 August 2003

**BEST AVAILABLE COPY**



18 JUL 02 17:34:17-2 D00571  
P01/7700 0.00-0216654.4

## Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

The Patent Office

Cardiff Road  
Newport  
South Wales  
NP10 8QQ

1. Your reference

PJS/ALP/P9065GB

2. Patent application number

(The Patent Office will fill in this part)

0216654.4

17 JUL 2002

3. Full name, address and postcode of the or of each applicant (underline all surnames)

Cambridge University Technical Services Limited  
16 Mill Lane  
Cambridge  
CB2 1SB

Patents ADP number (if you know it)

If the applicant is a corporate body, give the country/state of its incorporation

United Kingdom

8204724000

4. Title of the invention

CVD SYNTHESIS OF CARBON NANOTUBES

5. Name of your agent (if you have one)

W. H. Beck, Greener & Co.

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

W. H. Beck, Greener & Co.  
7 Stone Buildings  
Lincoln's Inn  
London WC2A 3SZ

Patents ADP number (if you know it)

323001

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country

Priority application number  
(if you know it)

Date of filing  
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing  
(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

Yes

- a) any applicant named in part 3 is not an inventor, or
  - b) there is an inventor who is not named as an applicant, or
  - c) any named applicant is a corporate body.
- See note (d))

**Patents Form 1/77**

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

Description 17

Claim(s) 5

Abstract

Drawing(s) 3 + 3

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (*Patents Form 7/77*)

Request for preliminary examination and search (*Patents Form 9/77*)

Request for substantive examination (*Patents Form 10/77*)

Any other documents  
(please specify)

11. I/We request the grant of a patent on the basis of this application.

Signature

Date 17.07.02

*Beck Green*

12. Name and daytime telephone number of person to contact in the United Kingdom

Mr. Peter J. Smart - (020) 7405 0921

**Warning**

*After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.*

**Notes**

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 08459 500505.*
- Write your answers in capital letters using black ink or you may type them.*
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.*
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.*
- Once you have filled in the form you must remember to sign and date it.*
- For details of the fee and ways to pay please contact the Patent Office.*

CVD SYNTHESIS OF CARBON NANOTUBES

The present invention relates to methods of synthesis of carbon nanoparticles, and to the carbon nanoparticles thus produced.

Carbon nanoparticles have received a great deal of attention since the discovery of the  $C_{60}$  buckminsterfullerene molecule (H. W. Kroto, J. R. Heath, S. C. O'Brien, R. F. Curl and R. E. Smally, *Nature* 318, 162 (1985)), and the carbon nanotube (S. Iijima, *Nature* 354, 56 (1991)). Carbon nanoparticles are typically 1 to 100 nm in at least one dimension, carbon nanotubes however being up to a few millimetres in length. The explosion in  $C_{60}$  research in the early 1990s was driven by the production of large quantities (few milligrams) of the material by Kratschmer et al. (W. Kratschmer, L. D. Lamb, K. Fostiropoulos and D. R. Huffman, *Nature* 347, 354 (1990)) using a high pressure arc discharge method.

The remarkable mechanical and electronic properties exhibited by carbon nanotubes have encouraged efforts to develop mass production techniques. As a result, carbon nanotubes are becoming increasingly available, and more attention from both academia and industry is focused on the application of carbon nanotubes in bulk quantities. These opportunities include the use of carbon nanotubes as a conductive filler in insulating polymer matrices, and as reinforcement in structural materials. Other potential applications exploit the size of carbon nanotubes as a template to grow nano-sized, and hence ultra-high surface-to-

volume ratio, catalysts or aim to combine carbon nanotubes to form nano-electronic elements.

The high cost and low production volume of carbon nanotubes are at present prohibitive for them to be used as a filler material in most large-scale structural and electrical applications. Presently, several industrial and governmental projects are underway to mass produce several kilograms of single and multi-walled carbon nanotubes in a cost-effective manner. For example, the National Institute of Materials and Chemical Research (NIMCR) and Showa Denko K. K. in Japan recently announced a project to develop a mass-production method to produce several hundred kilograms of nanotubes per day.

Carbon nanotubes have been produced previously using various approaches including the laser or arc-discharge ablation of a carbon/catalyst mixture target.

For larger scale synthesis, the most promising methods have been based on chemical vapour deposition (CVD). CVD typically uses a cheap feedstock and has relatively low energy requirements, and has therefore attracted interest for the purposes of bulk synthesis. In CVD methods, a carbon containing gas is decomposed at high temperatures under the influence of a finely divided catalyst (usually iron, nickel, cobalt or other transition metals or alloys).

Catalyst particles may be manufactured in situ by the decomposition of metalloorganic compounds or may be inserted into the CVD furnace on a fixed substrate (W. E. Alvarez et al., Carbon 39 (2001) 547-558; WO00/17102; WO00/73205). For the growth of small nanotubes and single-walled nanotubes in

particular, very small metal clusters (around 1 nm) are required.

The catalyst may be in the form of a fragmented surface layer on a porous or non-porous macroscopic substrate (Ren et al., Bower et al., V I Merkulov, D H Lowndes, Y Y Wei et al., Andrews et al., and Cui et al.). As described in Kanzow et al., the catalyst may be a laser ablated nickel target exposed to a flow of reactant gas.

Alternatively, the catalyst may be in finely divided form. In W000/17102, the catalyst is constituted by nanometer sized metal particles supported on larger (10-20 nm) alumina particles. The particles are placed in the centre of a furnace and the carbon containing gas is passed over them.

In W000/73205, catalyst particles comprising two different metals supported on silica, alumina, magnesia, zirconia or zeolite are used, again placed in a tube within a furnace. It is also suggested that the metallic catalytic particles may be continuously fed to the furnace.

Many catalyst precursors known in the art are initially contaminated with carbon-containing surfactants (e.g. Pluronic 123™) derived from precursor solutions. Carbon is removed by calcination at elevated temperatures (typically around 500 °C) in air, to produce an oxide. Alternatively, oxides or other inorganic salts which decompose to oxides (e.g. nitrates and carbonates) are used directly as catalyst precursors. In either case, it is then usual to reduce the oxide to the metal in a further step (typically 700 °C in hydrogen).

In W000/26138, catalyst nanoparticles are continuously produced within a furnace in the presence of reactant gas by decomposing a gaseous catalyst precursor (normally  $\text{Fe}(\text{CO})_5$ ) in the presence of a 'nucleation agency'. This may be a  
5 laser which provides some or all of the energy needed for photolysis of the catalyst precursor, or it may be a precursor moiety that stimulates clustering of catalyst atoms by decomposing more rapidly or binding to itself more strongly after dissociation. Typically, this is  $\text{Ni}(\text{CO})_4$ .

10 A continuing problem in this art is the control over the extent of the production of multi-walled nanotubes in preference to single walled nanotubes and the control of the diameter of the tubes. In CVD synthesis, fine structures, such as single walled nanotubes require very fine catalyst  
15 particles with diameters similar to that of the synthesised material (typically about 1 nm). Maintaining the required catalyst particle size generally requires the use of a substrate to act as a carrier material to stabilise the catalyst itself. However, the production of very fine  
20 supported catalyst particles prior to use in the nanotube synthesis is generally complex and expensive involving for example aggressive reagents and supercritical drying. Substantial problems arise in preventing nanoparticles from coalescing prematurely and the synthesis of such particles is  
25 not suitable for scaled-up production.

The production of catalyst particles in situ in the reaction zone as in W000/26138, where the catalyst particles are essentially unsupported, or where the nucleation of catalyst clusters is enhanced by the presence of Ni species  
30 suffers from a lack of particle size control. Since the

particles are growing, the time at which they initiate nanotube growth may be critical.

Because the nucleation sites are formed in situ from individual Ni atoms and comprise only a few atoms (2 to 5 atoms) in total, the process offers little control over the size of the nucleating "particle", or of the size of the final catalyst clusters. There is no controlled templating of the catalyst by the structure of the substrate.

In a first aspect, the present invention provides a method of production of carbon nanoparticles, comprising the steps of:

providing on substrate particles a transition metal compound which is decomposable to yield the transition metal under conditions permitting carbon nanoparticle formation;

contacting a gaseous carbon source with the substrate particles;

before, during or after the contacting step, decomposing the transition metal compound to yield the transition metal on the substrate particles and forming carbon nanoparticles by decomposition of the carbon source catalysed by the transition metal;

and

collecting the carbon nanoparticles formed.

The transition metal compound may contain more than one metallic element. Alternatively or additionally, a mixture of transition metal compounds may be used, and in this case the different transition metal compounds may contain different metallic elements.



Preferably, the transition metal compound is a transition metal salt. More preferably, the transition metal salt is a transition metal formate or oxalate.

The transition metal compound may be a transition metal carbonyl, more preferably a multi metal atom carbonyl. The transition metal carbonyls is preferably non-volatile, in the sense that it does not evaporate or sublime before decomposition takes place. The transition metal carbonyl may be a neutral compound or a salt. Preferred multi metal atom carbonyls contain from 13 to 55 metal atoms, for example a  $\text{Ni}_{38}$  carbonyl cluster. Suitable transition metal carbonyls for use in the invention may be made by the methods described in "Preparation, Characterisation and Performance of Encapsulated Copper-Ruthenium Bimetallic Catalysts Derived from Molecular Cluster Carbonyl Precursors." D. S. Shephard, T. Maschmeyer, G. Sankar, J. M. Thomas, D. Ozkaya, B. F. G. Johnson, R. Raya, R. D. Oldroyd, R. G. Bell, Chemistry Eu. J., 1998, 4, 1227; "Site-Directed Surface Derivatisation of MCM-41: Use of HRTEM and Molecular Recognition for Determining the Position of Functionality within Mesoporous Materials." D. S. Shephard, W. Zhou, T. Maschmeyer, J. M. Matters, C. L. Roper, S. Parsons, B. F. G. Johnson, M. J. Juer, Angew. Chem. Int. Ed., 1998, 37, 2718; "Preparation and Characterisation of a Highly Active Bimetallic (Pd-Ru) Nanoparticle Heterogeneous Catalyst." D. S. Shephard, R. Raja, G. Sankar, S. Hermans, S. Bromley, J. M. Thomas, B. F. G. Johnson, Chem. Comm. 1999, 1571; and "Supramolecular Ordering of Ruthenium Cluster Carbonyls in Mesoporous Silica." W. Zhou, D. S. Shephard, J. M. Thomas, T.

Maschmeyer, B. F. G. Johnson, R. G. Bell, Science, 1998, 280, 705.

Preferably, the transition metal is nickel, iron or cobalt.

5        Suitable carbon-containing compounds for use as the carbon source include carbon monoxide and hydrocarbons, including aromatic hydrocarbons, e.g. benzene, toluene, xylene, cumene, ethylbenzene, naphthalene, non-aromatic hydrocarbons, e.g. methane, ethane, propane, butane, pentane, hexane,  
10        cyclohexane, ethylene, propylene or acetylene, and oxygen-containing hydrocarbons, e.g. formaldehyde, acetaldehyde, acetone, methanol or ethanol, or a mixture of two or more thereof. In preferred embodiments, the carbon-containing compound is carbon monoxide (CO), methane, ethylene or  
15        acetylene.

Preferably, the gaseous carbon source is passed over the substrate particles.

The carbon source may be mixed with one or more gases acting as a diluent such as inert gases, e.g. argon. The  
20        carbon source may also be mixed with non carbon containing gases which play no direct role in the nanotube forming reaction but which play a contributory role, for instance by reacting with amorphous carbon as it is formed (as a by-product) and so keeping the reaction sites on the catalyst  
25        clean and available for nanotube formation.

Gases which may be mixed with the carbon source include argon, hydrogen, nitrogen, ammonia, carbon dioxide or helium.

Preferred gas pressures for the gaseous carbon source and optional diluent are from 0.1 to 50 bar A, preferably  
30        from 0.5 to 5 bar A, more preferably 1 to 2 bar A. The

gaseous effluent from the furnace may be recycled, with or without clean up.

The substrate particles are preferably a suspended finely divided substrate material. In the most straightforward case, the substrate particles are simply finely ground powders, for example oxides particles or silicate particles such as sodium chloride, silica, alumina,  $\text{CaSiO}_x$ , calcium oxide and/or magnesium oxide. Finer materials such as gels and aerogels may be generated by a range of methods known to those skilled in the art, such as fuming, colloidal processing, spray-drying, hydrothermal processing and so on. Particular benefit for the production of nanotubes may be derived by using structured substrate particles, particularly mesoporous silicas, anodised alumina membranes, or zeolites. These materials have channels of similar dimensions to nanotubes, and can further guide both the deposition of catalyst and synthesis of nanotubes.

The finely divided substrate particles preferably have a size not smaller than 1 nm, e.g. not less than 5 nm. They may contain not less than 10 atoms, e.g. not less than 15 to 20 atoms, perhaps not less than 50 atoms or 75 atoms.

Preferably, the transition metal compound is decomposed by heating, for example by heating to a temperature between 200 °C and 1000 °C, more preferably between 600 °C and 1000 °C. To stimulate decomposition of the catalyst precursor material, an additional energy source (over and above the temperature of the furnace) may be locally applied. The source must be able to penetrate the loaded substrate powder. Such a source is preferably an intense light source, for example a laser or an intense non-coherent light source such as a flash

In a second aspect, the second invention relates to a method of production of carbon nanoparticles, comprising the steps of:

- 5 providing on substrate particles a transition metal oxalate, formate or multi metal atom carbonyl;
- heating the transition metal oxalate, formate or multi metal atom carbonyl on the substrate particles;
- contacting a gaseous carbon source with the substrate particles; and
- 10 collecting the carbon nanoparticles formed.

The features described in connection with the first aspect of the invention may also be used in connection with the second aspect of the invention. In a particularly preferred embodiment of the second aspect of the invention, the  
15 transition metal oxalate, formate or multi metal atom carbonyl is nickel formate and the substrate particles comprise silica.

In a third aspect, the present invention relates to carbon nanoparticles formed by a method as described above.

- 20 The invention will be further illustrated by the following non-limiting examples, with references to the drawings, in which:

Figure 1 shows the apparatus used in Examples 1, 3, 4 and 6;

- 25 Figure 2 shows the product of Example 1:

- a) SEM image
- b) HRTEM image;

Figure 3 shows a Raman spectrum of the product of Example 2;

Figure 4 shows the product of Example 3:

- 30 a) SEM image

b) HRTEM image; and

Figure 5 shows the product of Example 4.

#### Apparatus

5

The apparatus 10 used in Examples 1, 3, 4 and 6 for the growth of carbon nanotubes is shown in Figure 1. The apparatus 10 comprises sources of argon 12, acetylene 14, hydrogen 16 and methane 18, connected to flow meters 20, 22, 24 and 26 respectively. Supply pipes 28, 30, 32 and 34 lead from sources 12, 14, 16 and 18 into a drying container 36 containing calcium chloride. The outlet 38 of the drying container 36 is connected to a horizontal furnace 40 with heating elements 42, 44. Catalyst 46 contained in an alumina crucible 48 is positioned in the furnace 40 aligned with the heating element 44. The outlet 50 of the furnace passes through a paraffin bubbler 52 and a beaker 54 containing activated carbon.

20 In Example 2, a modified version of the apparatus 10 of Figure 1 is used, wherein the furnace 40 is replaced by a quartz tube (not shown).

#### Example 1

25

100 mg of silica powder (fumed silica from Aldrich Chemical Company, surface area 200 m<sup>2</sup>/g) was placed in a flask. To this was added 4.0 ml of aqueous nickel formate ( $1.09 \times 10^{-2}$  M). The mixture was strongly stirred at room temperature for 30 30 minutes, then dried in an oven at 90 °C for 16 hours. The

growth. After 30 minutes of reaction, 25.37 mg of product was obtained. Raman spectroscopy indicated that the nanotubes were single-walled and monodisperse (Figure 3). The yield of the carbon nanotubes was 4.7 %, based on the formula:

$$\text{Yield \%} = (m_1 - m_0) / m_0 \times 100 \%$$

where:  $m_1$  is mass of the catalyst powder after growth  
 $m_0$  is mass of the catalyst powder after heating under identical conditions as for nanotube growth, except that no methane is introduced.

### Example 3

20 mg silica fine powder (fumed silica from Aldrich Chemical Company, surface area 200 m<sup>2</sup>/g) was placed in a flask. To this was added 1.5 ml aqueous nickel formate ( $3.8 \times 10^{-3}$  M). The mixture was strongly stirred at room temperature for 30 minutes, then dried in an oven at 90 °C for 16 hours. The prepared sample contained 1.7 wt% nickel loading relative to the silica support. The sample was ground gently by hand in an agate mortar to produce a uniform powder before introduction into the CVD furnace 40 (Figure 1) in an alumina crucible 48 for the growth of CNTs. The growth of CNTs was performed at 650 °C for 60 minutes using an acetylene and argon mixture (1:10 acetylene to argon). The total gas flow rate was 220 ml/minute. The products were characterised by SEM and HRTEM. Figure 4 shows SEM and HRTEM images of the MWNTs produced. The diameters of the nanotubes produced were typically about 10 nm.

Example 4

When hydrogen (5:5:1 ratio of argon to hydrogen to acetylene, total flow rate of 220ml/min) was added to the gas stream of Example 3 during growth, high yields of MWNTs were obtained (Figure 4). The diameters of the nanotubes were found to increase to about 22 nm.

Example 5

Nickel 38 carbonyl cluster is prepared from smaller clusters by reaction in base or with a molecular template. For example, nickel 38 carbonyl cluster is prepared from nickel tetracarbonyl via nickel 6 carbonyl cluster as follows.

Nickel tetracarbonyl (5 ml) and potassium hydroxide (13 g) in methanol were stirred for 24 h under nitrogen. The resulting deep red suspension was evaporated under vacuum and the residue was dissolved in water. Upon addition of solid potassium bromide (20 g) and further evaporation under vacuum to eliminate traces of methanol, red microcrystals of  $K_2[Ni_6(CO)_{12}] \cdot xH_2O$  (nickel 6 carbonyl cluster) were obtained. To synthesise nickel 38 cluster, nickel 6 carbonyl cluster is treated with either platinum (II) chloride or  $K_2PtCl_4$  in 1:1 molar ratio in acetonitrile. The  $Ni_{38}Pt_6$  carbonyl cluster salt can be separated from impurities as a result of differential solubility in the solvent.

Example 6

100 mg of silica powder (fumed silica from Aldrich Chemical Company, surface area 200 m<sup>2</sup>/g) is placed in a flask. To this is added 4.0 ml of dichloromethane dissolved nickel 38 carbonyl cluster ( $1.09 \times 10^{-2}$  M). The mixture is strongly stirred at room temperature for 30 minutes, then dried in an oven at 90 °C for 16 hours. The sample is ground gently by hand in an agate mortar to produce a uniform powder before, introducing into the CVD furnace 40 (Figure 1) in an alumina crucible 48 for the growth of CNTs. The growth of CNTs is performed using an argon-methane atmosphere (1:1 argon to 10 methane) with a total gas flow rate of 400 ml/minute. The temperature is 860 °C. After 30 minutes the products are characterised by scanning electron microscopy (SEM), high resolution transmission electron microscopy (HRTEM), and 15 Raman spectroscopy.

The one step process of the Examples is simple and cheap. The combinations of precursor and support particles used are particularly effective at producing high yields of 20 pure nanotubes.

Whilst the applicant does not wish to be bound by this theory, it is believed that the precursor molecules are adsorbed onto the surface of the support particles. At high temperatures the transition metal salt precursor of Examples 25 1 to 4 thermally decomposes to produce metal nanoparticles of 1 - 3 nm diameter and gaseous side products. Such nanoparticles are chemically very active and serve as a catalyst for CNT growth. Transition metal carbonyl cluster precursors decompose by loss of the surface and connecting 30 carbonyl ligands such that each cluster forms a metal



nanoparticle. Each metal nanoparticle is of suitable size to nucleate an individual nanotube.

In general larger catalyst particles suppress single wall carbon nanotubes. Large catalyst particles are produced  
5 by sintering. This occurs if the catalyst is held at high temperature, particularly where there are high metal loadings or a smooth surface on which metal particles are mobile. Where sintering occurs, multi wall carbon nanotubes or encapsulated nanoparticles tend to be formed, probably  
10 depending on the size difference between the catalyst and the fundamental support particles. A strong attraction between substrate and catalyst favours nanotube growth. Temperatures which are too high lead to overcoating and production of multi wall carbon nanotubes, nanofibres or vapour grown  
15 carbon fibres. In the processes of the examples there is no need for additional heat treatment that can give rise to undesirable sintering effects.

The processes of the invention as illustrated above have several advantages over known CVD processes. First, in the  
20 processes of the Examples, there is no need for the usual calcination and reduction steps to produce the catalyst from the catalyst precursor. Secondly, water is used as the solvent in preparation of the catalyst precursors of Examples 1 to 4, and may also be used in the preparation of catalyst  
25 precursors from transition metal carbonyl salts. The use of water rather than organic solvents has cost and environmental benefits. Thirdly, the precursors of Examples 1 to 4 are particularly easy to handle and to introduce onto the substrate as a result of their solubility in water,  
30 stability, low volatility, low cost and low toxicity. By

comparison, conventional precursors such as nickel tetracarbonyl are difficult to handle.

The process of Example 6 has the advantage that each transition metal carbonyl cluster forms a metal nanoparticle  
5 of defined size. This gives optimal control over nanotube diameter and may allow chirality control.

The process of the Examples can be used to produce high-quality, high yield SWCNTs on an industrial scale. The process may be scaled up in a number of ways. For example, a  
10 bed of supported catalyst may be fluidised using suitable carbon-containing gas and reacted product collected by elution due to its reduced effective density, whilst fresh supported catalyst precursor is continuously added. Alternatively, the supported catalyst precursor may be  
15 introduced to the top of a rotating, gently sloping cylindrical furnace tube and allowed to travel down the length of the heated furnace under a suitable atmosphere, growing nanotubes during the well-defined transit time. The quality of the nanotubes, in terms of diameter, length, ratio  
20 of SWNTs to MWNTs and amorphous carbon, can be controlled by controlling the catalyst loading, dispersion level in supports and the CVD growth parameters.

Although the invention has been described with reference to the Examples, it will be appreciated that various  
25 modifications are possible within the scope of the invention.

Claims:

1. A method of production of carbon nanoparticles,  
comprising the steps of:  
5 providing on substrate particles a transition metal  
compound which is decomposable to yield the transition  
metal under conditions permitting carbon nanoparticle  
formation;  
contacting a gaseous carbon source with the substrate  
10 particles;  
before, during or after said contacting step,  
decomposing the transition metal compound to yield the  
transition metal on the substrate particles;  
forming carbon nanoparticles by decomposition of the  
15 carbon source catalysed by the transition metal;  
and  
collecting the carbon nanoparticles formed.
2. A method as claimed in Claim 1, wherein the transition  
20 metal compound is a transition metal salt.
3. A method as claimed in Claim 2, wherein the transition  
metal salt is a transition metal formate or oxalate.
- 25 4. A method as claimed in Claim 1 or Claim 2, wherein the  
transition metal compound is a transition metal  
carbonyl.

13. A method as claimed in Claim 12, wherein the substrate particles comprise one or more of sodium chloride, silica, alumina,  $\text{CaSiO}_x$ , calcium oxide or magnesium oxide.

5 14. A method as claimed in any one of the preceding claims, wherein the substrate particles are in the form of a fumed powder, a colloid, a gel or an aerogel.

10 15. A method as claimed in any one of the preceding claims, wherein the transition metal compound is decomposed by heating.

15 16. A method as claimed in Claim 15, wherein the transition metal compound is decomposed by heating to a temperature between 200 °C and 1000°C.

20 17. A method as claimed in Claim 16, wherein the transition metal compound is decomposed by heating to a temperature between 600 °C and 1000 °C.

18. A method as claimed in any one of the preceding claims, wherein the carbon nanoparticles are carbon nanotubes.

25 19. A method as claimed in any one of the preceding claims, wherein the carbon nanotubes are single walled carbon nanotubes.

30 20. A method as claimed in any one of the preceding claims, further comprising the initial step of impregnating the substrate particles with the transition metal compound.

21. A method as claimed in any one of the preceding claims,  
where the method is continuous.

5 22. A method as claimed in Claim 21, comprising the steps of:  
continuously providing substrate particles;  
fluidising the substrate particles with a flow of gaseous  
carbon source;  
heating the transition metal compound on the substrate  
10 particles; and  
collecting the carbon nanoparticles formed by elution.

23. A method as claimed in Claim 21, comprising the steps  
of:

15 continuously providing substrate particles to an upper  
part of an inclined surface;  
contacting the substrate particles on the inclined  
surface with a flow of gaseous carbon source;  
heating the transition metal compound on the substrate  
20 particles; and  
collecting carbon nanoparticles formed from a lower part  
of the inclined surface.

24. A method of production of carbon nanoparticles,

25 comprising the steps of:  
providing on substrate particles a transition metal  
oxalate, formate or multi metal atom carbonyl;  
heating the transition metal oxalate, formate or multi  
metal atom carbonyl on the substrate particles;

contacting a gaseous carbon source with the substrate particles; and  
collecting the carbon nanoparticles formed.

- 5 25. A method as claimed in Claim 24, wherein the transition metal oxalate, formate or multi metal atom carbonyl is nickel formate and the substrate particles are silica particles.
- 10 26. Carbon nanoparticles formed by a method as claimed in any one of the preceding claims.



2/3




FIGURE 2




FIGURE 3



3/3




FIGURE 4




FIGURE 5

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☒ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**